


Peran PGF Floor Flakes

A decorative coating which contains varying sizes of flakes scattered over a coloured base coat and finished with a tough resistant clear sealer.



Attractive decorative finish:

Introduces texture and vibrancy into floors, gives extensive design potential



Wear resistance:

High scratch resistance and wear resistant surface for wheeled traffic; Ideal for public areas, shops and showrooms, department stores, designer outlets, restaurants, garden centres, airports, schools and hospitals



Seamless hygienic finish:

Easy to clean and maintain

Technical Information¹

REACTION TO FIRE

Class G	Certificate no 1721/75 SITAC
---------	---------------------------------

SLIP RESISTANCE²

Dry > 40	EN 13036-4
----------	------------

TEMPERATURE RESISTANCE

Up to 50°C

WATER PERMEABILITY

Karsten test - Nil (Impermeable)

WEAR RESISTANCE

AR2	PEN 13892-4
-----	-------------

VAPOUR PERMEABILITY

2,5 g/m ² /mm/24h	ASTM E96:90
------------------------------	-------------

FLEXURAL STRENGTH

> 15 N/mm ²	EN 13892-2
------------------------	------------

TENSILE STRENGTH

> 10 N/mm ²	BS 6319
------------------------	---------

IMPACT RESISTANCE

1 kg > 1,8 m 2 kg > 1,5 m	EN ISO 6272-1
------------------------------	---------------

BOND STRENGTH

Greater than cohesive strength of 25 N/mm² concrete (> 1,5 MPa)

SPEED OF CURE	10 °C	20 °C	30 °C
Light Traffic	24 hrs	12 hrs	6 hrs
Full traffic	72 hrs	48 hrs	24 hrs
Full chemical cure	12 days	7 days	7 days

Standard colour chart



Grey 1923

Red 5923

Grey 1924

Red 5914



Blue 2923

Blue 2914

Green 3923

Yellow 4913

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

¹ The figures in the table beside are typical properties achieved in laboratory tests – these results may vary depending on the conditions on the installation site.
² The final anti-slip properties of the floor are influenced by the application method, the size and shape of the aggregate used for the topcoat (aggregate recommendations available from Flowcrete Polska), the degree of abrasion, maintenance and the nature the dirt.

Model Specification

System:	Peran PGF Floor Flakes
Finish:	Gloss or Matt
Thickness:	Approx. 1,0 mm
Colour:	According to the catalog
Producer:	Flowcrete Group Ltd
Supplier:	Flowcrete Polska Sp. z o.o
Telephone:	+48 22 879 89 07

Installation Service

The installation should be carried out by a Flowcrete approved contractors with a documented quality assurance scheme. Obtain details of our approved contractors by contacting Flowcrete Polska or enquiring via our website at www.flowcrete.com.pl.

Products Included in this System

Primer + Flood Layer + Flakes²:	Flowseal EPW Peran Flakes
Sealer:	Peran STC
Sealer:	Flowseal PU Gloss

To make anti-slip stair edges please use Peran Sand Nr 8, ok. 0,25 kg/mb.

² If other resins are used contact Flowcrete Polska for further details.

Detailed application instructions are available upon request.


Substrate Requirements

Concrete or screed substrate should be class min. C20/25, a minimum bond strength of 1,5 MPa (pull-off test), surface even, clean, free from laitance, dust and other contamination. All damages in the substrate should be repaired prior to applying the flooring. The substrate should be dry up to 75% RH as per BS 8204 (5% moisture content per weight) and free from rising damp and ground water pressure. In case of higher humidity, one should use Hydraseal DPM as primer. Details to be found in the *Flowcrete Resin Flooring Substrate Requirements*.

Aftercare – Cleaning and Maintenance

Clean regularly manually or using a machine in conjunction with a mildly alkaline detergent. Flowcrete Flooring Cleaning Instruction available upon request.

System Design



Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless, impermeable surface with perfect adhesion to the substrate reduce the need for repairs and maintenance.

Technical information, recommendations and instructions concerning the product use, storage and maintenance included in this System Data Sheet are based on Flowcrete Polska Sp. z o.o. (further related as „Flowcrete”) knowledge and experience, reflecting the best acknowledged way of using the material for a given moment. Taking into consideration other factors that are beyond the producer’s control, including differences in quality of substrates, tools and other complementary materials, weather conditions, proper installation and also cleaning and maintenance, Flowcrete cannot take responsibility in case of failure to conform with information and instructions included in this System Data Sheet or, respectively, written recommendations from authorized Flowcrete representatives. One should always conform with up-to-date norms and building principles, and also safety, hygiene and health protection rules according to the information included in Material Safety Data Sheets and also on the products packaging. This System Data Sheet replaces all previous versions. In order to receive up-to-date System Data Sheets contact Flowcrete Polska

[25/01/18]

ООО “Реконструкция”
Россия, Санкт-Петербург,
Лабораторная улица Дом 10, офис
214
Тел: +7(812) 716-58-62
Email: info@peran.spb.ru

peran.spb.ru